

Test Report

Report No. A2180050586101001

Page 1 of 7

Applicant SEMIWARE SEMICONDUCTOR(SHANGHAI)CO.LTD**Address** NO.3387 SHENDU RODA PUJIANG MINHANG SHANGHAI CHINA**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client**

Sample Name(s) Polyer Positive Temperature Coefficient
Part No. SK6series、SK16series、SK30series、SK60series、SK72series、SK90series、SK130series、SK180series、SK240series、SK250series、SK400series、SK500series、SK600series
Sample Received Date Apr. 16, 2018
Testing Period Apr. 16, 2018 to Apr. 20, 2018

Test Requested As specified by client, to test Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent Chromium(Cr(VI)), Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers (PBDEs), Phthalates (DBP, BBP, DEHP, DIBP), Fluorine (F), Chlorine (Cl), Bromine (Br), Iodine (I) in the submitted sample(s).

Test Method/Test Result(s) Please refer to the following page(s).

Tested by

Verna

Reviewed by

Taoying

Approved by

Su Hongwei

Date

Apr. 20, 2018

Su Hongwei

Senior Laboratory Manager

No. R201808921

Centre Testing International Pinbiao(Shanghai) Co., Ltd.

No. 1996, Xinjinqiao Road, Pudong New District, Shanghai, China

检验检测专用章
Inspection & Testing Services

Test Report

Report No. A2180050586101001

Page 2 of 7

Test Method

Tested Item(s)	Test Method	Measured Equipment(s)
Lead(Pb)	IEC 62321-5:2013	ICP-OES
Cadmium(Cd)	IEC 62321-5:2013	ICP-OES
Mercury(Hg)	IEC 62321-4:2013	ICP-OES
Hexavalent Chromium(Cr(VI))	IEC 62321-7-1:2015	UV-Vis
	IEC 62321-7-2:2017 and/or determination of Total Chromium by IEC 62321-5:2013	UV-Vis/ICP-OES
Polybrominated Biphenyls(PBBs)	IEC 62321-6:2015	GC-MS
Polybrominated Diphenyl Ethers (PBDEs)	IEC 62321-6:2015	GC-MS
Phthalates (DBP, BBP, DEHP, DIBP)	IEC 62321-8:2017	GC-MS
Fluorine (F)	Refer to EN 14582:2016	IC
Chlorine (Cl)	Refer to EN 14582:2016	IC
Bromine (Br)	Refer to EN 14582:2016	IC
Iodine (I)	Refer to EN 14582:2016	IC

Test Result(s)

Tested Item(s)	Result		MDL
	001	002	
Lead (Pb)	N.D.	N.D.	2 mg/kg
Cadmium (Cd)	N.D.	N.D.	2 mg/kg
Mercury (Hg)	N.D.	N.D.	2 mg/kg
Hexavalent Chromium (Cr(VI))	N.D.	--	8 mg/kg
	--	N.D. ▼	0.10 µg/cm ² (LOQ)

Test Report

Report No. A2180050586101001

Page 3 of 7

Tested Item(s)	Result		MDL
	001	002	
Polybrominated Biphenyls(PBBs)			
Monobromobiphenyl	N.D.	N.D.	5 mg/kg
Dibromobiphenyl	N.D.	N.D.	5 mg/kg
Tribromobiphenyl	N.D.	N.D.	5 mg/kg
Tetrabromobiphenyl	N.D.	N.D.	5 mg/kg
Pentabromobiphenyl	N.D.	N.D.	5 mg/kg
Hexabromobiphenyl	N.D.	N.D.	5 mg/kg
Heptabromobiphenyl	N.D.	N.D.	5 mg/kg
Octabromobiphenyl	N.D.	N.D.	5 mg/kg
Nonabromobiphenyl	N.D.	N.D.	5 mg/kg
Decabromobiphenyl	N.D.	N.D.	5 mg/kg
Tested Item(s)	Result		MDL
	001	002	
Polybrominated Diphenyl Ethers (PBDEs)			
Monobromodiphenyl ether	N.D.	N.D.	5 mg/kg
Dibromodiphenyl ether	N.D.	N.D.	5 mg/kg
Tribromodiphenyl ether	N.D.	N.D.	5 mg/kg
Tetrabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Pentabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Hexabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Heptabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Octabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Nonabromodiphenyl ether	N.D.	N.D.	5 mg/kg
Decabromodiphenyl ether	N.D.	N.D.	5 mg/kg

Test Report

Report No. A2180050586101001

Page 4 of 7

Tested Item(s)	Result		MDL
	001	002	
Phthalates (DBP, BBP, DEHP, DIBP)			
Dibutyl phthalate (DBP) CAS#:84-74-2	N.D.	N.D.	50 mg/kg
Butyl benzyl phthalate (BBP) CAS#:85-68-7	N.D.	N.D.	50 mg/kg
Di-(2-ethylhexyl) phthalate (DEHP) CAS#:117-81-7	N.D.	N.D.	50 mg/kg
Diisobutyl phthalate (DIBP) CAS#:84-69-5	N.D.	N.D.	50 mg/kg

Tested Item(s)	Result		MDL
	001	002	
Fluorine (F)	N.D.	N.D.	10 mg/kg
Chlorine (Cl)	227 mg/kg	N.D.	10 mg/kg
Bromine (Br)	55 mg/kg	N.D.	10 mg/kg
Iodine (I)	N.D.	N.D.	10 mg/kg

Tested Sample/Part Description

- 001 Yellow body (Tested as a whole)
002 Silvery metal pin

Remark: The sample(s) had been dissolved totally tested for Lead, Cadmium, Mercury.

-MDL = Method Detection Limit

-N.D. = Not Detected (<MDL or LOQ)

-mg/kg = ppm = parts per million

-LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is 0.10 $\mu\text{g}/\text{cm}^2$

-▼ The sample is negative for Cr(VI) – The Cr(VI) concentration is below 0.10 $\mu\text{g}/\text{cm}^2$. The coating is considered a non-Cr(VI) based coating.

The sample(s) was tested as a whole, because it's impossible to disassemble or separate it by current equipment and technology. The result(s) shown on this report may be different from the content of any homogeneous material.


Test Report

Report No. A2180050586101001


Page 5 of 7

Test Process

1. Lead(Pb), Cadmium(Cd), Chromium(Cr)




2. Mercury(Hg)




3. Hexavalent Chromium(Cr(VI))

(1) IEC 62321-7-1:2015



(2) IEC 62321-7-2:2017




Test Report


Report No. A2180050586101001

Page 6 of 7


4. Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers (PBDEs)



5. Phthalates (DBP, BBP, DEHP, DIBP)



6. Fluorine (F),Chlorine (Cl), Bromine (Br),Iodine (I)




Test Report

Report No. A2180050586101001

Page 7 of 7

Photo(s) of the sample(s)



*** End of Report ***

Statement:

1. This report is considered invalidated without approval signature, special seal and the seal on the perforation;
2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. Without written approval of CTI, this report can't be reproduced except in full;
5. In case of any discrepancy between the English version and Chinese version of the testing reports (if generated), the Chinese version shall prevail.